



## CERAMIC FIBER PAPER

### Typical Parameters

Description	Std Paper	HP Paper
Classification Temperature (°C)	1260	1260
Max.Operating Temperature (°C)	1000	1100
Density (kg/m <sup>3</sup> )	200	250
<b>Chemical Composition (%)</b>		
Al <sub>2</sub> O <sub>3</sub>	47	48
SiO <sub>2</sub>	52	51
Fe <sub>2</sub> O <sub>3</sub>	<<0.5	<<0.5
Na <sub>2</sub> O	<<0.2	<<0.2
<b>Physical Properties</b>		
Organic Content (%)	<<9	
Color	White	
Loss of Ignition (%)	<<10	
Tensile Strength (Mpa)	>>0.3	

We updated the products information constantly and confirmed with us or our distributor the validity of the current data sheets herein the TDS before relying on any data or other information in this product information sheet. A product sheet that has been superseded may contain incorrect, obsolete and /or irrelevant data and other information.

MCC ENGINEERING provides its catalog,handbooks, and any other printed materials for your general guidance. The MCC does not guarantee that the information contained within them, including but not limited to, the contents of any page that resides under the Domain Name System (DNS) registration of [www.mccengineering.com.my](http://www.mccengineering.com.my) is up-to-date,complete and accurate, and individuals assume any risks associated with relying upon information without checking other credible sources,MCC reserves the right to make changes to any provision or requirement within these sources.