

## VACUUM FORMED SHAPE Typical Parameters

Description	VFS1260	VFS-1430	VFS-1500	VFS-1600
Classification temperature (°C)	1260	1430	1500	1600
Density (kg/m <sup>3</sup> )	250~400			
Linear Shrinkage after Heating (%)	<<3(1100°C)	<<3(1200°C)	<<3(1350°C)	<<3(1400°C)
<i>Specific size can be produced according to customer requirements.</i>				

We updated the products information constantly and confirmed with us or our distributor the validity of the current data sheets herein the TDS before relying on any data or other information in this product information sheet. A product sheet that has been superseded may contain incorrect, obsolete and /or irrelevant data and other information.

MCC ENGINEERING provides its catalog,handbooks, and any other printed materials for your general guidance. The MCC does not guarantee that the information contained within them, including but not limited to, the contents of any page that resides under the Domain Name System (DNS) registration of [www.mccengineering.com.my](http://www.mccengineering.com.my) is up-to-date,complete and accurate, and individuals assume any risks associated with relying upon information without checking other credible sources,MCC reserves the right to make changes to any provision or requirement within these sources.